

低周波シールド対応 鉄-ニッケル合金めっき用添加剤

Additive for Iron-nickel Alloy Plating For Low Frequency Waves

トップフェニックLFS TOP FENICK LFS

●浴安定性に優れる実用的な鉄-ニッケル合金めっき液

Practical iron-nickel alloy plating, great bath stability

●鉄含有率20%(最大45%)の低応力な光沢めっき皮膜が得られる

Iron content in the deposition films 20% by weight (maximum 45%), low film stress can be obtained

●低周波領域でシールド効果が向上

Improve shield effect at low frequency waves

標準処理条件

Standard condition

皮膜の鉄含有率:20%

Iron content in the deposition films


硫酸ニッケル六水和物 Nickel (II) sulfate hexahydrate	180g/L
塩化ニッケル六水和物 Nickel (II) chloride hexahydrate	45g/L
硫酸第一鉄七水和物 Iron(II) sulfate hydrate	40g/L
ホウ酸 Boric acid	40g/L
トップフェニックLFS-S TOP FENICK LFS-S	5ml/L
トップフェニックLFS-G TOP FENICK LFS-G	40ml/L
アクナH ACNA H	3ml/L
陰極電流密度 Cathode current density	6A/dm ²
pH	2.2
浴温 Bath temperature	40°C

引っ張り応力 : 48MPa
Tensile stress

電流効率 : 97%
Current efficiency

低周波シールド効果が向上

Improve shield effect to low frequency waves



シールド材試験方法: KEC法
Shield material test method

めっき膜厚: 15μm(両面)
Film thickness

method

Both sides

素材: 銅板(t0.3mm)
Substrate: Copper plate

優れた浴安定性

Great bath stability

トップフェニックLFS

TOP FENICK LFS



沈殿なし
No precipitation



沈殿あり
Precipitation


めっき液外観の比較
Comparison of solution appearance

浴安定性に優れ、管理が容易

Great bath stability, easy bath control

安定した鉄合金比率

Stable iron content in the deposition films



幅広い電流密度で
鉄含有率20%前後を維持
Maintain about 20% iron content in the deposition films
at wide current density areas